

ALAG®

ALAG® 0-4 mm

ALAG® 4-10 mm

1 Description

ALAG® is a hard, dense and heat resistant aggregate used in areas where exceptional durability is required. It is a synthetic calcium aluminate, with an alumina content of approximately 40%. ALAG® is used with calcium aluminate cements, such as CIMENT FONDU® to give a concrete with superior wear resistance in arduous applications.

CIMENT FONDU®/ALAG® concrete combines high early strength with excellent long term properties. It resists abrasion, impact and corrosion as well as tolerating high temperatures and thermal shock / cycling.

Concretes based on CIMENT FONDU® and ALAG® aggregate are ideally suited to the most demanding applications:

- Industrial floors subject to heavy-duty attack: food processing, chemical or petrochemical, iron, steel and non-ferrous metallurgical industries.

- Hydroelectric structures: high abrasion areas in flumes and spill-ways.

- Sewerage network protection: pipes, manholes and associated structures.

It is particularly well suited for the following uses:

- Work requiring very high early mechanical strength.
- Resistance to corrosion by dilute acids (pH > 3.5), sulphates, oils, industrial wastes and aggressive water.

- Areas subject to abrasion, erosion and impact. CIMENT FONDU®/ALAG® concrete offers within few hours superior strength and durability compared with concretes based on Portland cement and hard aggregates such as granite and basalt.

- Cryogenic applications (e.g. concrete areas subject to liquid gas spillage).

- Applications which need to withstand high temperature (up to 1100°C) and thermal shock.

Alag® is produced and controlled within a quality management system that is certified according to ISO 9001.

2 Specifications

The specification limits indicated are determined with an acceptable quality level (AQL) of 2.5% as defined in the sampling standard ISO 3951.

Usual values represent typical values of our production.

Chemical Analysis

Principal constituents (%)	Usual values	Specification limit
Al ₂ O ₃	37.5 - 43.5	> 36.0
CaO	35.0 - 40.0	< 42.0
SiO ₂	3.0 - 5.0	< 6.0
Fe ₂ O ₃	14.0 - 18.0	< 18.5

- Chemical analysis is determined according to EN 196-2.
- Tests conducted prior to crushing and classification.

Particle size distribution ALAG® 0-4 mm

Sieve size	Cumulative % Passing	
	Usual values	Specification limit
4 mm	95 - 100	> 95
2.5 mm	68 - 88	
1 mm	32 - 54	
500 µm	20 - 34	
200 µm	7 - 17	
100 µm	1 - 9	< 15

Particle size distribution ALAG® 4-10 mm

Sieve size	Cumulative % Passing	
	Usual values	Specification limit
12.5 mm	100	
10 mm	84 - 100	> 84
8 mm	55 - 81	
6.3 mm	33 - 63	
5 mm	15 - 35	
4 mm	6 - 14	< 20

3 Additional data

This information is given for guidance only.

Physical properties

- Open porosity: none
- Hardness (Mohs): 7 - 8
- Density : 3.25 g/cm³
- Bulk density :
 - ALAG[®] 0-4mm :1650 - 1700 kg/m³
 - ALAG[®] 4-10mm :1600 - 1650 kg/m³

4 Concrete/mortar properties

This information is given for guidance only.

Technical data on CIMENT FONDU[®]/ALAG[®] concrete

- Water/cement ratio < 0.40
- Composition : See "mix design"

	Mechanical strength at 20°C		
	1 day	7 days	28 days
Compressive (MPa)	50	60	70

♦Tests conducted on 16 x 32 cm cylinders according to NF P 18 406

♦CIMENT FONDU[®]/ALAG[®] concrete is subject to the conversion phenomenon; only strength after conversion should be considered for design purpose.

	Strength after heating Treatment temperature		
	110°C	800°C	1100°C
Flexion (MPa)	9.0	6.5	3.2
Compression (MPa)	95	72	23

♦Tests conducted on 40x40x160mm prisms; All samples immersed in water for 24 hours then held for 24 hours at 110 °C; remaining samples held at 800 °C or 1100°C and then cooled slowly.

Kerneos warrants that the products comply with the specifications stated herein to the exclusion of any other warranty, express or implied. Kerneos makes no representation or warranty of any kind, either express or implied, as to the merchantability or fitness for a particular purpose or use of the products. The warranty shall be limited to the replacement of the non-conforming products or, at Kerneos' option, the refund of the purchase price. Any technical advice, recommendations or information are given based Kerneos' current knowledge and experience of the products and are deemed to be accurate. However, Kerneos undertakes no liability or responsibility of any kind in respect thereof. Users are invited to check that they have the latest version of this document.

The compressive strength of CIMENT FONDU[®]/ALAG[®] concrete develops in a similar way to concretes made with CIMENT FONDU[®] and natural aggregates, including the fact that it is subject to the conversion phenomenon. See the CIMENT FONDU[®] Product Data Sheet for more information.

CIMENT FONDU[®]/ALAG[®] concrete gives exceptional high strengths within 24 hours after placing. This feature is useful to ensure fast return to service which allows a reduction in the overall downtime.

Guidance on the correct application of CIMENT FONDU[®]/ALAG[®] concrete is available from our technical department.

Mix Design

The mix design employed when using CIMENT FONDU[®]/ALAG[®] concrete will depend on the type of application, thickness of the concrete, method of placing, and degree of workability required.

Typical composition of mortars and concretes per cubic metre:

		CIMENT FONDU [®]	ALAG [®] Fine 0 - 4 mm	ALAG [®] Coarse 4 - 10 mm
Mortar Thickness < 50 mm	Parts by weight	1	3	-
	Dosage	600 kg	1800 kg	-
Concrete Thickness > 50 mm	Parts by weight	1	2	2
	Dosage	515 kg	1030 kg	1030 kg

- ♦Yield based on a water/cement ratio of 0.40
- ♦These typical mix design are given for guidance only

5 Storage

ALAG[®] must be stored in dry conditions off the ground.